

---

**Product Description**

---

**ELOTEX<sup>®</sup> FL2200** is a non-defoamed redispersible polymer powder based on the copolymer of vinyl acetate and ethylene, especially developed for self leveling flooring compounds. ELOTEX<sup>®</sup> FL2200 is formaldehyde free, low emissions product allowing for formulating to EMICODE EC1<sup>PLUS</sup> requirements.

Protective colloid	Polyvinyl alcohol
Additives	Mineral anti-block agents

---

**Specifications**

---

Appearance	free-flowing, white powder
Bulk density	500 - 630 g/l
Residual moisture	< 1.0 %
Ash TGA 1000°C	10.5% +/- 1.5 %
pH value	6.5 – 8.0 (as a 10% dispersion in water)
Min. film building temp.	+ 3°C
Film properties	opaque, viscoplastic

---

**Application Areas**

---

For modification of hydraulically and non-hydraulically curing systems. ELOTEX<sup>®</sup> FL2200 is especially developed for the manufacture of flooring systems that must comply with EMICODE EC1<sup>PLUS</sup> requirements and have especially low formaldehyde levels.

**Main application areas**

- Highly recommended for fluidized bed adhesives
- Use in systems containing cement and gypsum in floor applications
- Self-levelling floor levelling compounds, particularly casein-free systems
- Ideal for use in manually and pump applied finished products

---

**Key Attributes**

---

**During processing**

- Excellent rheology and workability
- Greatly improved flow and levelling properties
- Excellent surface self-levelling and merging on pump processing of fluid floor compounds
- Improved water retention capability
- Reduced water demand
- Fluidizing consistency
- Ideal wetting behavior
- Optimum levelling behavior and good compatibility with synthetic levelling agents
- Fast redispersibility
- Very low emission

**In the cured state**

- High final strengths
- High cohesive force (cohesion)
- Increased adhesive bond strength (adhesion)
- Increased flexibility
- Improved freeze-thaw cycling resistance
- Optimization of abrasion and impact resistance
- Reduction of shrinkage and cracking

---

**Powder Processing**

---

ELOTEX<sup>®</sup> redispersible powders can be blended in all commercial positive mixers with other dry additives to produce finished products in powder form. Since ELOTEX<sup>®</sup> redispersible powders exhibit thermoplastic behaviour, mixing times should be as short as possible, and significant temperature rise caused by strong shear forces should be avoided. All hydraulically and non-hydraulically curing dry mixtures with ELOTEX<sup>®</sup> redispersible powder may be easily mixed with water before application.

For mixing finished products in powder form, one usually places the required amount of mixing water in a suitable vessel and add the powder mixture under agitation. Too intensive agitation of the mixture may result in unwanted air inclusion. Before application, one should allow the mixture to stand for a short time. Depending on the properties of the other additives, the standing time will be in the range of approx. 1-5 minutes.

---

**Packaging and Storage**

---

Standard packaging: 25 kg paper sacks with polyethylene liners.

Other types of packaging such as Big Bags or silo wagons are possible on request.

As a basic rule it is recommended to store ELOTEX<sup>®</sup> redispersible powder in a dry location at temperatures below 25°C and to process within six months. Sacks that are stored under pressure, damaged or left open for an extended period tend to cause blocking of the redis-persible powder.

---

**Quality, Safety and Environment**

---

ELOTEX<sup>®</sup> redispersible powders are non-toxic and are unclassified according to Regulation 88/379/EEC. We recommend all individuals using ELOTEX<sup>®</sup> redispersible powder, or coming in contact with it, to observe the separate Safety Data Sheets. Our safety specialists will be pleased to advise you regarding safety, health and environmental issues of our products. Akzo Nobel Chemicals AG has been certified according to DIN EN ISO9001 and DIN EN ISO 14001.

---

**Product Liability**

---

The above information and recommendations are based upon our experience and are offered merely for advice. They do not absolve the consumer from making his own tests. Akzo Nobel Chemicals AG, their representatives or distributor organizations have no control over the conditions under which ELOTEX<sup>®</sup> redispersible powders are transported, stored, handled or used. Responsibility for damage arising from the use of our products cannot be derived from the recommendations given. The observance of any intellectual property rights of third parties is the responsibility of the consumer in each case.

Technical information may not be passed on to any third party without our previous consent.

---

**Other Information**

---

Version	1 / 1.9.2014
Replaces version from	-
Date of issue	1.9.2014

Akzo Nobel Chemicals AG  
Industriestrasse 17a, CH-6203 Sempach Station  
T +41 41 469 69 69 F +41 41 469 69 00  
[contact.elotex@akzonobel.com](mailto:contact.elotex@akzonobel.com) [www.akzonobel.com/elotex](http://www.akzonobel.com/elotex)

**AkzoNobel**